



## Description

Blackbutt is a coarse-textured, strain-grained timber typical of the harsh Australian coastal climate in which it thrives. It's hard and tough but relatively easily worked – qualities that have made it a popular choice for decking. Blackbutt is honey blonde coloured and its sapwood is resistant to borers. Heartwood pale brown, but northern material may sometimes display a pinkish tinge. Sapwood distinctively paler. Texture medium and even. Grain usually straight. Gum veins common.

### Botanical Name

*Eucalyptus pilularis*

### Origin of Timber

NSW, QLD

### BAL

Bushfire Attack Level 12.5, 19 & 29

All AS 3959 Required Applications

## Suitability

- Doors
- Boating
- Cabinet door
- Decking and cladding
- Flooring and staircase
- Furniture
- Joinery

## Technical Information

Tangential Shrinkage	7.3%
Radial Shrinkage	4-5%
Unit Movement	0.37%
Density per Standard	900 kg/m <sup>3</sup>
Modulus of Rupture	144 MPa
Modulus of Elasticity	19 GPa
Maximum Crushing Strength	77 MPa
Impact	22 joules (J)
Toughness	Medium 15-25 Nm
Hardness	9.1 kN