



Description

The heartwood of Blue Gum ranges in colour from dark pink to reddish brown. The paler sapwood is readily distinguishable. Grain is typically straight with occasional interlocking. Texture is moderately coarse and gum veins are common.

Botanical Name

Eucalyptus saligna

Origin of Timber

NSW, QLD, NZ

BAL

Bushfire Attack Level 12.5 & 19

All AS3959 Required Applications

Suitability

- Doors
- Boating
- Cabinet door
- Decking and cladding
- Flooring and staircase
- Furniture
- Joinery

Technical Information

Tangential Shrinkage	9.5%
Radial Shrinkage	>5%
Unit Movement	0.35%
Density per Standard	850 kg/m ³
Modulus of Rupture	140 MPa
Modulus of Elasticity	18 GPa
Maximum Crushing Strength	68 MPa
Impact	18 joules (J)
Toughness	Medium 15-25 Nm
Hardness	9 kN