



Description

Silvertop Ash has a narrow sapwood, which is not clearly distinguishable from the heartwood. Its heartwood is brown and sometimes pinkish in colour and often features the grain interlocked with growth rings. With a medium texture, silvertop ash is also recognisable by the common occurrence of gum veins, the markings of pinhole borers and pencil streaks.

Botanical Name

Eucalyptus sieberi

Origin of Timber

NSW, VIC, TAS

BAL

Bushfire Attack Level 12.5, 19 & 29

All AS3959 Required Applications

Suitability

- Flooring
- Furniture
- Joinery
- Decking & Cladding

Technical Information

Tangential Shrinkage	10.6%
Radial Shrinkage	>5%
Unit Movement	0.36%
Density per Standard	850 kg/m ³
Modulus of Rupture	136 MPa
Modulus of Elasticity	17 GPa
Maximum Crushing Strength	70 MPa
Impact	20 joules (J)
Toughness	Medium 15-25 Nm
Hardness	9.5 kN