



Description

Jarrah is renowned for its rich red colours that deepen over time. The heartwood ranges from deep browns to burgundy hues. Jarrah sapwood exhibits shades from pale yellow to pink-orange. The timber displays a moderately coarse and even textured grain. The occasional incidence of wavy and interlocking grain produces some samples with a sought after fiddle-back figure.

Botanical Name

Eucalyptus marginata

Origin of Timber

Western Australia

BAL

BAL 12.5 and 19 – All AS3959 required applications, BAL 29 – Decking (in conjunction with non-combustible wall cladding and enclosed subfloor).

Suitability

- Flooring
- Lining
- Decking
- Cladding
- Furniture
- Stairs
- Joinery

Technical Information

Tangential Shrinkage	7.4%
Radial Shrinkage	4-5%
Unit Movement	0.3%
Density per Standard	800 kg/m ³
Modulus of Rupture	112 MPa
Modulus of Elasticity	13 GPa
Maximum Crushing Strength	61 MPa
Impact	10 joules (J)
Toughness	Low – up to 15 Nm
Hardness	8.5 kN