



## Description

Tasmanian oak is light in colour, varying from straw to reddish brown with intermediate shades of cream to pink. It is recognised for its excellent staining qualities, which allow ready matching with other timbers, finishes or furnishings.

### Botanical Name

Eucalyptus delegatensis, Eucalyptus obliqua & Eucalyptus regnans

### Origin of Timber

Tasmania

### BAL

Not Tested

## Suitability

- Cabinet Door
- Flooring & Staircase
- Furniture
- Joinery
- Framing
- Cladding

## Technical Information

Tangential Shrinkage	8.5%
Radial Shrinkage	>5%
Unit Movement	0.35%
Density per Standard	650 kg/m <sup>3</sup>
Modulus of Rupture	110 MPa
Modulus of Elasticity	19 GPa
Maximum Crushing Strength	70 MPa
Impact	18 joules (J)
Toughness	Medium – 15 to 25Nm
Hardness	5.7 kN